

BN COMPONENTS

Boron Nitride Ceramic Components

TECHNICAL DATA

Boron nitride is a high temperature ceramic that has a structure similar to graphite. Our portfolio of hot-pressed solid materials includes pure hexagonal boron nitride as well as composites suitable for applications requiring excellent thermal properties combined with electrical isolation. Easy machinability and fast availability make boron nitride an outstanding choice for prototypes to large quantities requiring its unique properties.

GENERAL PROPERTIES

- High thermal conductivity/thermal shock resistance
- Electrical isolation/high electrical resistivity
- Non-wetting to glass and metals/corrosion resistant

APPLICATIONS

- Furnace insulators/muffles/crucibles
- Molten metal
- Hall effect thrusters
- Semi-conductor/plasma
- Powder metal atomization
- Sintering setters

Material Type	Boron Nitride						Boron Nitride Composites			
	BN4000	BN5000	BN6000	BN7000	BN8000	BN9000	BNP-2	BNP-3	BNP-6	PBN
Grade	BN4000	BN5000	BN6000	BN7000	BN8000	BN9000	BNP-2	BNP-3	BNP-6	PBN
Composition	hBN (B ₂ O ₃ binder)	hBN (CaO + B ₂ O ₃ binder)	hBN	hBN	hBN	hBN	AlN+BN	BN 45% ZrO ₂ 45% SiO ₂ 10%	BN 43% ZrO ₂ 4% SiO ₂ 53%	—
Maximum Service Temperature, °C	850 Air, 1200 Inert	850 Air, 1150 Inert	850 Air, 2000 Inert	850 Air, 2000 Inert	850 Air, 1700 Inert	850 Air, 1900 Inert	1020 Air, 1900 Inert	850 Air, 1600 Inert	1000+	850 Air, 2000 Inert
Density, g/cm ³	2.0	2.0	1.9	1.9	1.3	1.6	2.9	2.9	2.1	1.9–2.1
Flexural Strength(RT), MPa	94 /65 ±	59 /45 ±	14 /30 ±	22 /21 ±	42 /40 ±	22 /21 ±	300	144 /07 ±	>50	115
Compressive Strength, MPa	143 /186 ±	97 /97 ±	40 /40 ±	25 /25 ±	20 /20 ±	18 /18 ±	<1070 /<1070 ±	218 /253 ±	312 /312 ±	—
C.T.E 20°C–1000°C x10 ⁻⁶	1.9 /1.8 ±	1.5 /0.10 ±	5.5 /1.0 ±	1.6 /0.4 ±	1.6 /1.2 ±	0.2 /0.3 ±	0.57 /0.46 ±	0.51 /4.2 ±	>2.5 />2.0 ±	15.5 “c”, 3.0 “a” (-40–150°C)
Thermal Conductivity, W/m*K	30 /34 ±	27 /29 ±	21 /21±	78 /130 ±	30 /30 ±	36 /36 ±	92.6 /92.6 ±	24-34 /24-34 ±	—	1.6 “c”
Dielectric Strength, KV/mm	88	>10	>70	79	—	—	—	—	—	230 “c”
Volume Resistivity, ohms*cm	>10 ¹³	>10 ¹³	10 ¹⁴	>10 ¹⁴	>10 ¹⁵	>10 ¹⁵	—	—	—	10 ¹⁵

NOTES:

- The values indicated above are for reference and subject to change.
- Compressive Strength listed is Typical Value.

Boron Nitride Materials Applications

Grade	General Properties	Applications
BN4000	With the boric oxide binder, BN4000 has the highest mechanical properties of all the pure hBN products. BN4000 can be used in a variety of electrical insulator and general-purpose applications. The hygroscopic nature of boric oxide makes this material susceptible to moisture pick-up.	High-temperature electrical insulators, Crucibles, Ion implantation systems, Powdered metal spray nozzles, Setter plates
BN5000	The calcium borate binder in BN5000 makes this the most versatile of all the hBN grades due to the reduced susceptibility to moisture pick-up. BN5000 can be used in a variety of higher temperature applications where lower thermal expansion and higher thermal shock resistance are required.	Thermocouple protection tubes, Crucibles, Electrical insulators, Glass manufacturing rolls and support plates
BN6000	Having one of the lowest binder contents of all the hBN materials, BN6000 offers an economical alternative to the high purity grades. BN6000 is an excellent general-purpose grade for use in higher temperature applications requiring vacuum or inert environments in sizes up to ø300mm x 400mm long.	Electrical insulators, Thermocouple protection tubes, Crucibles and rollers for molten glass and metals, Casting Nozzles for non-ferrous metals, Channel and pump components for molten metals
BN7000	When high purity, binder-less and the highest temperature capability are required, BN7000 offers the best of all hBN grades. With a use temperature up to 2000° C in inert atmospheres or high vacuum, BN7000 can be used in the most extreme conditions.	Insulators for high temperature vacuum furnaces, Crucibles for high purity metals and Refractories, High-temperature electrical insulators
BN8000	This low density hBN grade incorporates unique near-net shape forming and pressure-less sintering technology, allowing sizes up to ø350mm x 200mm long or 490mm x 300mm x 50mm. BN8000 offers all the expected properties of thermal shock resistance, electrical resistivity, and chemical inertness.	High-temperature and high-voltage electrical insulators, Thyristors electrical insulators
BN9000	A medium density version of hBN, BN9000 utilizes unique near-net shape forming and pressure-less sintering technology, allowing sizes up to 490mm x 310mm x 50mm. The large size capability makes it an excellent choice for furnace setters requiring all the benefits of hBN.	Insulators, Semiconductor equipment, Jigs for molding glass, Nozzles and crucibles, Paving plates
BNP-2	For applications requiring high thermal conductivity, BNP-2 offers the benefits of an aluminum nitride in a composite with boron nitride. BNP-2 offers excellent mechanical strength while still maintaining ease of machinability and is useful for a broad range of applications.	Vacuum furnace seals, Nuclear, Casting nozzles, High-temperature bearings
BNP-3	Combining boron nitride with zirconia and silicon carbide gives BNP-3 outstanding performance in molten metal applications. The non-wetting, wear-resistant, and high strength properties of BNP-3 make it ideal for break rings and atomizer nozzles.	Molten metal side dams, Continuous casting break rings, Refractories, Crucibles, Atomizing nozzles
BNP-6	Excellent electrical properties combined with resistance to moisture and thermal shock are primary benefits of the BNP-6 composite of boron nitride and silica. BNP-6 has superior mechanical strength and is easily machinable for applications including Hall effect thrusters and refractory applications requiring corrosion resistance.	Aerospace / Satellite Thrusters, Plasma, Extreme environments, PVD: constraint of Plasma arcs, Extreme corrosion and wear resistance
PBN	Unique in its structure and ultra-high purity, Pyrolytic BN (PBN) is a grade of boron nitride grown by Chemical Vapor Deposition. PBN can be machined from flat plate stock up to 3mm thick or produced in custom shapes such as crucibles for semiconductor and crystal growth applications.	MBE crucibles, MBE furniture, Electrical insulators, Vacuum furnace insulation, LEC, VGF, Crucibles, Heating element supports

Kennametal manufactures sophisticated materials in the form of castings, powders, coatings, consumables, and machined parts that resist wear, corrosion, and abrasion. Information provided in this document is intended only for general guidance about Kennametal. Selection and purchase of Kennametal products is the sole responsibility of the product user. Individual applications must be fully evaluated by the user, including compliance with applicable laws, regulations, and non-infringement. Kennametal cannot know or anticipate the many variables that affect individual product use and individual performance results may vary. For these reasons, Kennametal does not warrant or guarantee information in this document and assumes no liability regarding the same. Kennametal makes no warranties regarding this information and disclaims all express or implied warranties with respect to this information, including, without limitation, all implied warranties of merchantability and fitness for a particular purpose and warranties of patent non-infringement. Kennametal will not be responsible for special, incidental, exemplary, or consequential damages that may be incurred pursuant to the use of the information provided in this document. To learn more, please contact your local Kennametal sales office.

Sales Offices

Americas
Tel: 800 458 3608
americas.sintec@kennametal.com

United Kingdom (UK)
Tel: +44 (0)1633 63 65 00
emea.sintec@kennametal.com

Europe/Middle East/Africa
Tel: +49 (0)8861 2308 0
emea.sintec@kennametal.com

Asia Pacific
Tel: 852 2572 8991
ap.sintec@kennametal.com

China
Tel: +86 21 3718 0518
ap.sintec@kennametal.com



kennametal.com